



TRUEBOARD

EXPANDED POLYSTYRENE INSULATION

PROPERTIES

Material Details	Nominal Density kg/m ³	Flame Spread	Smoke Developed
25 min (min)	16	260	over 400
25 min (min)	24	240	over 490
25 min (min)	32	230	over 670

- Expanded polystyrene foamed plastic in the form of board insulation.
- Classified as to surface burning characteristics in accordance with CAN/ULC-S102.2M.
- Density values given for reference purposes only and are not included in the CAN/ULC-S701 Standard.
- Values quoted are max values for 25 mm thick sample. Lower values will result for thicker materials.